

GRANIITBETOON

GRANITE CONCRETE M 500

CAST CONCRETE BASED ON CRUSHED GRANITE

Compressive strength class C45/50 EVS-EN 206-1:2014

**Good weather-resistance, extra strong cast concrete.
Used in places where weight is a major concern.**

**For casting staircases, lintels, concrete belts, levelling courses assembling works of cast concrete details.
For correcting assembling defects.**

Used indoors and outdoors.

NB! In winter concrete is produced for use in temperatures of up to -10° C

COMPOSITION

Crushed granite (4-8 mm), quartz sand, Portland cement, plasticizers.

PREPARATIONS

Pour the necessary amount of powder into a mixer or mixing unit.
Add water 10-14% of powder weight (2.5-3.5 litres per 25 kg bag).
Mix mechanically or manually until thoroughly wet.
Working time of ready-made mix is 1 hour.

STORAGE

Store bagged powder in dry conditions.
Storage time is up to 1 year.